

PAROC UNS 37

General insulation slab



Certification Number	0809-CPR-1015 / VTT Expert Services Ltd, P.O. Box 1001, FI-02044 VTT, Finland, 18.12.2013
Designation Code	MW-EN13162-T4-DS(70,-)-WS-WL(P)-MU1
Short Description	Flexible, fire safe stone wool slab with high thermal insulation and sound absorption performance.
Application	General-purpose insulation product for thermal, sound and fire insulation in external walls, lofts and floors in all kind of buildings.

PAROC stone wool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200°C. The insulating properties remain unchanged, but the compressive stress weakens. The softening temperature of stone wool products is over 1000°C.

Dimensions

Dimensions	
Width x Length	Thickness
610 x 1220 mm	40 - 250 mm
In accordance with EN 822	In accordance with EN 13162

Dimensional Stability		
Property	Value	According to
Dimensional Stability at Specified Temperature (Declared), DS(70,-)	≤ 1 %	EN 13162:2012 (EN 1604)

Other Dimensions Other sizes available on request.

Packaging

Package Type Plastic Package or Big Pack

Fire Properties

Reaction to Fire Declared		
Property	Value	According to
Reaction to Fire, Euroclass	A1	EN 13162:2012 (EN 13501-1)

Continuous Glowing Combustion		
Property	Value	According to
Continuous Glowing Combustion	NPD	EN 13162:2012

Other Fire Properties		
Property	Value	According to
Combustibility	Non-combustible	EN ISO 1182

Thermal Properties

Thermal Resistance		
Property	Value	According to
Thermal Resistance	See attachment	EN 13162:2012
Thermal Conductivity λ_D	0,037 W/mK	EN 13162:2012 (EN 13162)
Thickness Tolerance, T	T4	EN 13162:2012 (EN 823)

Direct Airborne Sound Insulation Index		
Property	Value	According to
Air Flow Resistivity AF_R	NPD	EN 13162:2012 (EN 29053)

Moisture Properties

Water Permeability		
Property	Value	According to
Water Absorption, Short Term W_S, W_p	$\leq 1 \text{ kg/m}^2$	EN 13162:2012 (EN 1609)
Water Absorption, Long Term $W_L(P), W_{lp}$	$\leq 3 \text{ kg/m}^2$	EN 13162:2012 (EN 12087)

Water Vapour Permeability		
Property	Value	According to
Water Vapour Transmission MU, μ	1	EN 13162:2012 (EN 12086)

Sound Properties

Acoustic Absorption Index		
Property	Value	According to
Sound Absorption	NPD	EN 13162:2012 (EN ISO 354)

Emissions

Release of Dangerous Substances to the Indoor Environment		
Property	Value	According to
Release of Dangerous Substances	NPD	EN 13162:2012

Durability

Durability of Reaction to Fire Against Heat, Weathering, The fire performance of mineral wool does not deteriorate with time. The Euroclass classification of product is related to the organic content, which cannot increase with time.

Ageing/Degradation

Durability of Thermal Resistance Against Heat,
Weathering, Ageing/Degradation

Thermal conductivity of mineral wool products does not change with time, experience has shown the fibre structure to be stable and the porosity contains no other gases than atmospheric air.

Head Office: PAROC GROUP, P.O. Box 240 (Energiakuja 3), FI-00181 Helsinki Finland, Tel. +358 46 876 8000, www.paroc.com

The information in this brochure describes the conditions and technical properties of the disclosed products, valid at the time of publication of this document and until replaced by the next printed or digital version. The latest version of this brochure is always available on the Paroc website. Our information material presents applications for which the functions and technical properties of our products have been approved. However, the information does not mean a commercial guarantee. We do not assume liability of the use of third party components used in the application or the installation of our products. We cannot warrant the suitability of our products if used in an area or conditions which are not provided in our information material. As a result of constant further development of our products we reserve the right to make alterations to our information material at any time. PAROC is a registered trademark of Paroc Group. This data sheet is valid in following countries: international use (general information).